Asbestos rubber sheet



Other name in world: Asbestos Jointing Sheet,

Compressed Asbestos Fiber Jointing Sheet,

CAF Gasket Sheet, Asbestos Sheet, Asbestos Jointing

Paronite,

Made of asbestos Fibre, rubber and heat-resisting packing material, compressing it to thick paper .Used for the equipment in water, steam, etc. and used as sealing material in the joints of pipeline.

 $This \ series \ include: XB150, XB200, XB250, XB300, XB350, XB400, XB450, XB510.$

With steel wire inserted and coated with graphite on the surface is applicable

Available Sizes:

Thickness: 0.3 to 6mm

4500 x 1500mm, 4100 x 1500 mm, 3850 x 1300 mm, 3810 x 2700 mm 1500 x 2000 mm, 1500 x 1500 mm, 1500 x 1350 mm, 1500 x 1000 mm,

1270 x 1270 mm,

The other size is optional or according to the requirements of customers.

Packing: in roll or in wooden pallet of about 1000 kgs, 2000kgs net each.

Products data sheet

GB/T 3985---2008

Item		XB510	XB450	XB400	XB350	XB300	XB250	XB200	XB150
Tensile strength MPa≥		21	19.0	15.0	12.0	9.0	7.0	6.0	5.0
Burning Loss %≤			28		30				
Compressibility %		7 ~ 17							
Rebound degree		45			40			35	
Creep Stress-relaxation≤		50							
Aging Coefficient ≥		0.9							
Density g/cm³		$1.9 \sim 2.0$							
Normal temperature Pliability		Bend 180 degree on the round column (the column diameter is 12 multiple sample thickness), No crack							
Nitrogen leakage rate [(ml/h.mm)] ≤		500							
Steam Airtightness	Temperature °C	500~510	440~450	390~400	340~350	290~300	240~250	190~200	140~150
	Steampressure MPa	13~14	11~12	8~9	7~8	4~5	3~4	2~3	1.5~2
	Request	Keep for 30 minutes without Leakage							